

Technical Data Sheet

Everlast

Description

Diamond Everlast emulsion is based on PVA copolymer binder which gives good flow and smooth matt finish.

Recommended use

Recommended for use on plaster, concrete, gypsum, brickwork and asbestos surfaces. This product is recommended for interior use only.

Physical properties

Colour	Standard Colour Range
Finish	Matt
Solids (vol %)	44 ± 2
Flash point	None – water based
Specific Gravity	1.40 – 1.60

Film Thickness and Spreading Rate

Film Thickness	30 microns dft
Theoretical Spreading Rate	13 - 15(m ² /l)

Surface Preparation

All loose material including loose plaster, cement splashes, old paint, dust, etc. must be thoroughly removed. New plaster / concrete must be fully cured.

Application data

Application Method	Spray (airless or conventional), Brush, Roller
Thinner/Cleaner	Clean water
Thinning	50 - 70% with clean water

Drying Time

Temperature	Dry to touch	Dry to handle	Recoating Time
25 °C	30 minutes	2 hours	3 hours
35 °C	15 minutes	1 hour	2 hours

Typical paint system

On Plaster / Concrete

Diamond Overall Wall Sealer	1 Coat
Diamond Overall Primer Filler Putty	2 Coats
Diamond Everlast Emulsion	3 Coats

Everlast Emulsion



Storage

The product must be stored in accordance to national regulations. The product should be kept in a well-ventilated place, protected from heat and direct sunlight. The containers must be kept tightly closed.

Handling

Handle with care. Stir well before use.

Packing Size

3.64 Ltrs, 14.56 Ltrs.

Health and Safety

Material health and safety datasheet is available upon request. Please observe the precautionary notice displayed on the container. Ensure proper ventilation during application and drying of paint. Avoid inhalation of paint mist and vapours and skin contact. Spillage of paint on skin should immediately be removed with suitable cleanser soap and water. Eyes should be well flushed with water and immediate medical attention should be sought.



The No. 1 Selling National Brand