

# Technical Data Sheet

Ace Timberlac Series

## Description

Diamond Ace Timberlac Sanding Sealer is a Protective Nitrocellulose based sanding sealer.

## Recommended use

Diamond Ace Timberlac Sanding Sealer is recommended to use on wood and wooden products to fill the pores in order to get the better finish.

## Physical properties

Colour	Pale Yellow, Dried film transparent
Finish	Satin
Solids (vol %)*	36 ± 2
Flash point	40 °F
Specific Gravity	0.95 – 1.00

## Film Thickness and Spreading Rate

Film Thickness	30 microns dft
Theoretical spreading rate	13 (m <sup>2</sup> /l/ coat)

## Surface Preparation

Ensure surface is dry and free from oil, grease, dust etc.

## Application

Application Method  Spray (airless or conventional)  
Muslin Cloth Pad

Thinner/Cleaner Diamond Ace Timberlac Premium Thinner

Thinning 40 - 50 %

## Drying Time

Temperature	Dry to Touch	Dry to Handle	Recoating Time
25 °C	20 minutes	4 hours	1 hour
35 °C	15 minutes	3 hours	40 minutes

## Typical paint system

### On wood

Diamond Ace Timberlac Sanding Sealer	Several coats to attain smooth finish
Diamond Ace Timberlac Gloss Lacquer	2 Coats
Or	
Diamond Ace Timberlac Matt Lacquer	2 Coats

## Ace Timberlac Sanding Sealer



## Storage

The product must be stored in accordance to the national regulations. The product should be kept in a well-ventilated place, protected from heat and direct sunlight. The containers must be kept tightly closed.

## Handling

Handle with care. Stir well before use.

## Packing Size

0.91 Ltr, 3.64 Ltrs, 20 Ltrs.

## Health and Safety

Material health and safety data sheet is available upon request. Please observe the precautionary notice displayed on the container. Ensure proper ventilation during application and drying of paint. Avoid inhalation of paint mist and vapours and skin contact. Spillage of paint on skin should immediately be removed with suitable cleanser soap and water. Eyes should be well flushed with water and immediate medical attention should be sought.



The No. 1 Selling National Brand